

Materials Needs for Future In-Space Propulsion Systems

Les Johnson, Leslie Alexander, Roy Young and Erin Richardson
NASA George C. Marshall Space Flight Center, Alabama 35812

Kyle Frame
Gray Research, Inc., Huntsville, AL 35806

Abstract

NASA's In-Space Propulsion Technology Project is developing the next generation of in-space propulsion systems in support of robotic exploration missions throughout the solar system. The propulsion technologies being developed are non-traditional and have stressing materials performance requirements. (Chemical Propulsion) Earth-storable chemical bipropellant performance is constrained by temperature limitations of the columbium used in the chamber. Iridium/rhenium (Ir/Re) is now available and has been implemented in initial versions of Earth-Storable rockets with specific impulses (I_{sp}) about 10 seconds higher than columbium rocket chambers. New chamber fabrication methods that improve process and performance of Ir/Re and other promising material systems are needed. (Solar Sail Propulsion) The solar sail is a propellantless propulsion system that gains momentum by reflecting sunlight. The sails need to be very large in area (from 10000 m² up to 62500 m²) yet be very lightweight in order to achieve adequate accelerations for realistic mission times. Lightweight materials that can be manufactured in thicknesses of less than 1 micron and that are not harmed by the space environment are desired. (Aerocapture) Blunt Body Aerocapture uses aerodynamic drag to slow an approaching spacecraft and insert it into a science orbit around any planet or moon with an atmosphere. The spacecraft is enclosed by a rigid aeroshell that protects it from the entry heating and aerodynamic environment. Lightweight, high-temperature structural systems, adhesives, insulators, and ablatives are key components for improving aeroshell efficiencies at heating rates of 1000-2000 W/cm² and beyond. Inflatable decelerators in the forms of ballutes and inflatable aeroshells will use flexible polymeric thin film materials, high temperature fabrics, and structural adhesives. The inflatable systems will be tightly packaged during cruise and will be inflated prior to entry interface at the destination. Materials must maintain strength and flexibility while packaged at cold temperatures (-100°C) for up to 10 years and then withstand the high temperatures (500°C) encountered during aerocapture.

Introduction

Future in-space propulsion systems will be quite different from any flown before. This change will be necessitated by the nature of our exploration of the solar system – all the “easy” destinations have been surveyed. Future science and exploration missions will carry more payload, visit more propulsive-intense destinations, survey multiple targets per mission, or some combination thereof. This will drive the propulsion requirements

away from today's state-of-the-art (SOA) chemical propulsion systems and toward those with higher performance, or, in some cases, toward non-traditional propulsion technologies such as solar sails and aerocapture.

Advanced Chemical Propulsion Technologies and Systems

Chemical systems have traditionally provided the primary means of spacecraft propulsion. However, today's SOA systems are nearing their theoretical performance limits. Near-term solutions must provide improvements that can not only meet these needs but also offer benefits that can be translated into new science. In response, SOA systems must evolve to meet the ever more demanding missions of the aerospace community.

Increases in earth storable bipropellant rocket performance can be achieved by modifying some combination of the following variables: geometric or mechanical design, thruster operating conditions, or propellant. Changes to operating conditions, e.g. higher chamber pressure or mixture ratio, increase the chamber combustion gas temperature and yield higher wall temperatures. These higher wall temperatures must be addressed through improvements in thermal design. Hence, performance can be significantly impacted by the realization of gains from improved materials properties and manufacturing processes. For chemical systems, the temperature limitations of columbium (niobium) used in the fabrication of traditional thrust chambers place performance constraints on the propulsion system that can be mitigated through alternate material selection. Incorporating high temperature, oxidation resistant combustion chamber materials, such as Iridium/Rhenium (IrRe), into innovative designs can mitigate the impact of higher heat fluxes without compromising engine characteristics or performance.

However, the performance potential for IrRe thrust chambers has not been fully exploited. Advanced IrRe thrust chamber materials offer increases in I_{sp} that approach 10 to 20 seconds over those SOA columbium designs. Further improvements in system performance can be harnessed without compromising risk. To achieve higher I_{sp} , it is possible to operate at higher temperatures -- in the 2800 K range. This requires materials that can be manufactured to withstand the higher combustion temperatures. Analytical and test data suggest that successfully enduring higher temperatures would expand the operating range of existing designs and provide increased margins for chamber pressures and mixture ratios. By modifying mixture ratio and increasing chamber pressure, more aggressive performance targets can be met. This translates directly into kilograms of payload mass.

Factors that affect the operating temperature of IrRe chambers include rhenium purity and porosity. To facilitate technology advancements, investigating in alternative manufacturing processes is key to improving the quality and reducing the cost of fabricating thrust chamber assemblies. Hardware suppliers can now fabricate many propulsion components that can withstand these higher temperatures. Using processes such as electroforming and vacuum plasma spray has the potential to reduce cost, decrease cycle time, and improve both producibility and reliability.

With the current knowledge base, low risk, low cost improvements that capitalize on the significant investments, and the progress made-to-date, addressing component high temperature needs is desirable. The potential for growth in this area will have immediate benefits to flight engines for DoD, NASA and commercial applications. Advanced material engine development can demonstrate the full performance capability of the Ir/Re (or similar) material system and pave the way to higher pressure systems and subsequent high performance storable propellant engines that could be enabling for many mission destinations.

Solar Sail Propulsion Systems

A solar sail is a propellantless propulsion system that gains momentum by reflecting sunlight. Though simple in concept, engineering a solar sail space propulsion system will be challenging. High residual velocities can only be reached by a solar sail if the specific ratio of spacecraft weight and sail size (sail area density) is very small. The sails need to be very large in area (from 10000 m² up to 62500 m²) in order to achieve adequate accelerations for realistic mission times.

The SOA solar sail systems produced for the NASA In-Space Propulsion Technology Program's 20 meter Ground System Demonstrations (GSD), seen in Figure 1, were 2 micron thick Mylar and CP1^{1,2}. While Mylar is commercially available in thickness as low as 0.9 micron and is inexpensive, the material is susceptible to solar UV radiation. CP1 is much more tolerant of the space environment; however the variation in material




Figure 1: L'Garde (left) and ATK (right) 20 meter GSD in the 33-m diameter Space Power Facility vacuum chamber at the NASA Glenn Research Center's Plum Brook Station.

thickness and material costs may prohibit its use on large solar sails. Lightweight materials that can be manufactured in thicknesses of less than 1 micron and that are not harmed by the space environment are required for future solar sail missions such as Interstellar Probe (ISP)³ where the required sail areal density is ~ 1g/m².

In addition to the sail substrate, innovative coatings that provide the reflective surface and thermal control of the solar sail are also required. Coating processes used on the 20-meter GSD's left many pinholes and variations in the coating thickness, which could result in unwanted radiation exposure of the base substrate. New coatings that reflect

better than 89% of the incident sunlight over a broad spectral range and high emissivity backside coatings, including carbon black nanotubes, for temperature control are desired.

Novel concepts to provide lighter sails involve the removal of the heaviest sub-system of a sail as currently conceived, namely the sail substrate. Assuming that a plastic backing is only needed during the manufacturing and assembly phases for handling and the launch phases to prevent the very thin aluminum film from cracking along the fold lines when in the stowed configuration, three solutions have been suggested for the on-orbit removal of that substrate⁴:

- 1) The mechanical removal of the plastic material, perhaps using a laser beam controlled to a nanometric precision that can ablate the plastic substrate once in orbit
- 2) The use of a plastic material undergoing photolysis reaction under the effect of the light of the sun
- 3) Thermally removing the plastic film.

Boom materials should combine high strength and stiffness with extremely low density and compactness ratios for stowage within a very tight volume for launch. The 20 meter GSD demonstrated graphite coilable booms (ATK) and inflatable, thermally rigidized booms (L'Garde). Research into thinner graphite protruded rods, possibly incorporating integrated active damping elements to control structural modes, and investigations into other novel composite materials such as carbon fiber reinforced plastic are desired. Several classifications of rigidizable materials have been identified over the last several decades that provide a wide range of performance characteristics⁵. These rigidizable materials, being composite in nature, are compiled of various matrix materials (the materials responsible for the rigidization), reinforcements, and supporting polymer film layers. Investigations into variations and combinations of these materials to provide a wide range of performance characteristics that can be tailored to the solar sail mission environment are also desired.

Aerocapture Systems

The rigid aeroshell is considered the first generation Aerocapture technology. The second generation technology is the inflatable decelerator. The In-Space Propulsion Technology Project has been funding development of three inflatable decelerator systems: the trailing ballute, the afterbody attached ballute, and the forebody attached inflatable aeroshell.

The trailing ballute (Figure 2A) features an inflated toroid that is much larger than the spacecraft it is towed behind and is used similarly to a parachute to slow the vehicle. The toroidal shape was selected to allow the hole in the toroid to "swallow" the spacecraft wake. Approximately 24 hours before the spacecraft interfaces with the planetary atmosphere, the ballute is deployed and allowed to fully inflate. This precludes problems the system would encounter during inflation in the atmosphere. The trailing ballute design allows for easy detachment and minimizes interference with the spacecraft's operation. Trajectory control is simply through drag modulation. When the spacecraft

achieves a predetermined deceleration, the ballute is released, allowing the spacecraft to exit the atmosphere. A propulsive periapsis raise maneuver is required to circularize the orbit.




Figure 2: Trailing Ballute (A); Afterbody Attached Ballute (B); Forebody Attached Inflatable Aeroshell (C)

The afterbody attached ballute (Figure 2B) is much like the towed ballute except that the ballute is attached directly to the back of the spacecraft. Again trajectory control is through drag modulation and the ballute is released when a certain deceleration is achieved.

The forebody attached inflatable aeroshell (Figure 2C) is more evolutionary to the rigid aeroshell. The inflatable aeroshell is often referred to as a hybrid system, with a rigid foreshell and an inflated, attached ballute extending from the front of the spacecraft. Trajectory control for the inflatable aeroshell will incorporate lift and drag, like the rigid aeroshell system; therefore the characterization that the system is more evolutionary than the drag-only modulated systems.

Inflatable decelerator systems provide performance advantages over the rigid aeroshell design. One such advantage is that the payload does not need to be enclosed in a rigid aeroshell system during interplanetary cruise. Eliminating the rigid aeroshell allows the spacecraft payload to take full advantage of the volume available in the launch vehicle shroud due to packaging efficiencies enabled by the inflatable systems. Also, with a rigid aeroshell design, the system must fly low into the atmosphere submitting the spacecraft to significant entry heating. With the inflatable decelerator designs, the spacecraft stays higher in the atmosphere where the density is less and heating can be an order of magnitude (or more) lower than with a rigid system, allowing any protection around the payload to be very lightweight. The trailing and attached ballute systems are designed to stay much higher in the atmosphere where heating on the system can be below $5\text{W}/\text{cm}^2$. This low heating enables the system design to keep surface temperatures below 500°C . The inflatable aeroshell may fly deeper into the atmosphere so it will be designed for higher heating rates (on the order of tens of W/cm^2) and slightly higher surface temperatures.

Materials of interest for Aerocapture inflatable decelerators are lightweight, high temperature capable fabrics, fibers, polymers, adhesives. These materials must withstand

being tightly stowed during transit through the cold vacuum of space for many years, even decades, without losing ductility or strength. Major materials concerns include polymeric materials becoming creased during stowage leading to weak points that fail during deployment, or structural adhesives becoming embrittled due to exposure to the cold (-100°C) temperatures and ultraviolet radiation of space. Another concern is that the polymeric materials will degrade during transit causing the material to stick to itself and not deploy. Additionally, there is the overarching fear that the maximum temperature exposures will lead to failure of all the materials. Preliminary tests indicate these concerns may not be founded, but much more work needs to be performed to truly retire the risk.

If the above mentioned concerns are in fact problems, there may be options to address them. Some such options could be coatings or other surface treatments to alter the mechanical, physical or optical properties of the materials. Another option involves the addition of localized thermal protection system materials being applied in high heat flux or high temperature regions. Some novel alternatives include designing material laminates that degrade at a known rate. If structural adhesives cannot be determined to have the necessary mechanical properties at both low and high temperatures, then alternative seaming techniques, such as sewing or mechanical fastening, will need to be investigated.

Summary

While much more mature than just a few years ago, various new in-space propulsion systems and technologies would benefit from materials improvements related to increasing their performance. The highest-priority needs for each propulsion system can best be summarized as follows:

Advanced Chemical Propulsion

- High-temperature resistant thrust chamber materials

Solar Sail Propulsion


- Light-weight substrates and booms

Aerocapture

- Storable lightweight, high temperature capable fabrics, fibers, polymers, and adhesives

References

-
- ¹ Murphy, D.M., "Validation of a Scalable Solar Sailcraft," *53rd Joint Army-Navy-NASA-Air Force (JANNAF) Propulsion Conference*, December; 2005.
- ² Lichodziejewski, D., Derbès, B., Galena, D., Friese, D., "Vacuum Deployment and Testing of a 4-Quadrant Scalable Inflatable Rigidizable Solar Sail System," AIAA 2005-3927, *Joint Propulsion Conference*, July, 2005.
- ³ Sauer, C. G., "Solar sail trajectories for solar polar and interstellar probe missions," AAS 99-336, *AAS/AIAA Astrodynamics Specialist Conference*, August, 1999.
- ⁴ Scaglione, S., Vulpetti, G., "The Aurora Project: Removal Of Plastic Substrate to Obtain an All-Metal Solar Sail," *Acta Astronautica*, Vol. 44, Nos. 2-4, pp. 147-150, 1999.
- ⁵ Cadogan, D. P., Scarborough, S. E., "Rigidizable Materials for use in Gossamer Space Inflatable Structures," AIAA 2001-1417, *42nd Structures, Structural Dynamics, and Materials Conference & Exhibit*, April, 2001.



Materials Needs for Future In-Space Propulsion Systems

National Space & Missiles Materials Symposium
2006

Presented By






Les Johnson, Manager


USFC Space Science Programs & Projects Office

Co-Authors

David Alexander, Bonnie James, Erin Richardson

Boyd Young, and Randy Baggett





Advanced Propulsion Technology Program Will Develop New Propulsion Systems for Robotic Exploration of the Solar System



TRL 9

TRL 8

TRL 7

TRL 6

TRL 5


TRL 4

TRL 3

TRL 2


TRL 1

NASA Implementation: (Deep Space One Ion Engine Example)






Aerocapture

Solar Sails





Solar Electric Propulsion





In-Space Propulsion Technologies

Adv. Chemical

Tethers



Low-TRL Technologies For the Future



External Pulsed Plasma

Fusion & Antimatter


Beamed Energy

Not Within ISP Scope

The Art of Aerocapture



How atmospheric drag
can be used to slow
an interplanetary
spacecraft and
capture it
into orbit





Basics of Orbit Capture





1. Aerobraking maneuver
(no propulsive)

2. Aerobraking maneuvers
(orbit period reduction
following propulsive
capture)


3. Aerocapture maneuver
(immediate science
orbit establishment from
hyperbolic approach)

INCREASING BENEFIT
FROM THE ATMOSPHERE





Aerocapture



Technology Description:


Aerocapture technology uses the atmospheres of planets and moons to reduce the speed of a vehicle and capture it into a quick, near-propellantless orbit capture. The atmosphere is used as a brake, transferring the kinetic energy associated with the vehicle's high speed into heat.

Advantages:

- Reduces the delta V at target arrival
- Reduces mission cost
- Reduces the time to enter orbit (helps for time sensitive Earth return or emergency)

Challenges and Research Needs:


- High speed entry and deceleration
- High speed entry and deceleration
- High speed entry and deceleration



All values are compared to the mass of an all-propellant capture. Equivalent ΔV from Aerocapture noted above each column.

Technology Area Status

- Four awards developing advanced TPS concepts, structures and adhesives to enable a low cost aeroshell with integrated TPS - hardware development and tests are underway
- Trade Studies, conceptual design, and hardware development and testing in the areas of aerodynamic deceleration, heating, catalytic attachers, inflated and inflatable structures
- Inflated and rigid structures, inflatable structures, and aeroshell development and testing




Aerocapture Technology Alternatives



(Higher Maturity)


Blunt Body Designs



- Low to moderate maturity
- Provides increased tolerance for navigation and atmospheric uncertainties
- Provides increased volume and improved packaging advantages for larger spacecraft


(Lower Maturity)

Trailing Ballutes




- Low maturity
- Applicable to all size and shape payloads
- May have performance advantages over Blunt Body, such as not having the payload enclosed during interplanetary cruise

Attached Ballutes



- Low to moderate maturity for Earth and Mars
- Developed and launched in 1996 by Soviet Union as part of Mars Global Surveyor mission. Launch did not fail.
- Investigating key technology for aerocapture, precision landing, and control
- High performance



Rigid Body Aerocapture Materials Challenges



Extremely high flow velocities
result in rich variety of
thermodynamic phenomena
which drive material challenges.

They include:


- Oblique Shock Waves
- Subsonic, Supersonic, Transonic,
and Hypersonic and Hypersonic Flows
- Nonequilibrium Gas Chemistry
- Convective and Radiative Heat-
Transfer

•Materials challenges include:

- Lightweight, high-temperature structures,
adhesives, insulators, and ablatives
operating with heating rates of 1000-
2000 W/cm² and beyond.
- Minimize Heat Flux
- Very Thin Materials
- Significant Tensile Strength at Very High
Temperatures
- High Emissivity
- Low Thermal Expansion



Inflatable Body Aerocapture Materials Challenges




•Materials challenges include:

- Survive being tightly-packaged for years during mission cruise and then being quickly inflated
- Maintain strength and flexibility at -100°C during cruise and then withstand 500°C during aerocapture



Solar Sail Propulsion





Solar Sails



- Solar sails use photon pressure force on thin, lightweight reflective sheet to produce thrust. Sails open up new regions of the solar system to accessibility for important science missions, with no propellant required.












Image courtesy of NASA/JPL






Solar Sails



Technology Area Status:

- Two parallel awards to design, fabricate, and test competing sail concepts for system level ground demonstration
 - 10 m system ground demonstrators were developed and tested in 2004
 - 20 m system ground demonstrators designed, fabricated, and tested in thermal vacuum conditions in 2005
- Multiple awards to develop and test high fidelity computational models of sail dynamics
- Multiple awards for development of optical properties measurement and effects characterization ground demonstration




Solar Sails Materials Challenges



Materials challenges include:



- Must be fabricatable in sizes from 10000 m² to 1000000 m²
- Temperature Tolerance -70 - 2000 °K (0.0003 - 0.25 AU)
- Density - 0.4 - 0.9 gm/m²
- Tensile Strength (2-500 °K) 2205 MPa
- Gamma and UV Radiation Tolerance

- Low Coefficient of Thermal Expansion 3×10^{-6} (per °C)
- Sail Fabric Areal Density 0.5 gm/m²
- Fabric Thickness < 0.35 mm (polyimide II = 1.4 gm/m²)
- Sail Structure Areal Density 0.5 gm/m²




ADVANCED CHEMICAL PROPULSION

Advanced Propellants • Lightweight & Optimized Components





Advanced Chemical Propulsion



Problem Statement / Technology Status

Current state of transportation for space payloads is limited by the performance of chemical rocket systems are at or near current technology performance limits

Current state of systems, solid, storable liquid, and cold gas, as well as liquid propellants, as well as hybrid and monopropellants, and cold gas rockets

Project Objectives

Performance Objectives

Develop and demonstrate a new propulsion system that will provide a significant performance improvement over current state of the art systems

Benefits






- Reduced cost
- Reduced propulsion system mass
- Increased payload mass fraction
- Improved propellant performance and safety
- Improved overall efficiency for thermal engines, propellant management, and meteoroid and debris shielding systems

Lightweight & Optimized Components

Develop and demonstrate a new propulsion system that will provide a significant performance improvement over current state of the art systems



Advanced Chemical Propulsion





Advanced Propellants:

Advanced chemical propulsion systems that offer significantly improved performance and reliability through technologies that enable long-term storage and operation in low g.


Lightweight Components:

Optimized component, material and manufacturing technology to reduce the mass of cross-cutting propulsion components: feed system components, tanks, etc.

Space Transportation ZBO vs. Passive
670 kg LH2, LEO Mass Comparison



Active mixture ratio control results in a 56% increase in science payload





Advanced Chemical Propulsion Materials Challenges



- **Materials challenges include:**

- Survive being tightly-packaged for years during mission cruise and then being quickly inflated
- Maintain strength and flexibility at -100°C during cruise and then withstand 500°C during aerocapture

1. The first step in the development of a new propulsion system is the selection of the mission requirements. This includes the destination, the required thrust, the required specific impulse, and the required mass flow rate. 2. The second step is the selection of the propulsion system. This is based on the mission requirements and the available technology. 3. The third step is the design of the propulsion system. This includes the selection of the engine, the selection of the nozzle, and the selection of the fuel. 4. The fourth step is the construction of the propulsion system. This includes the fabrication of the engine, the fabrication of the nozzle, and the fabrication of the fuel system. 5. The fifth step is the testing of the propulsion system. This includes the testing of the engine, the testing of the nozzle, and the testing of the fuel system. 6. The sixth step is the flight of the propulsion system. This includes the launch of the vehicle, the operation of the propulsion system, and the landing of the vehicle. 7. The seventh step is the evaluation of the propulsion system. This includes the evaluation of the performance, the evaluation of the reliability, and the evaluation of the cost. 8. The eighth step is the improvement of the propulsion system. This includes the improvement of the engine, the improvement of the nozzle, and the improvement of the fuel system. 9. The ninth step is the development of a new propulsion system. This includes the selection of the mission requirements, the selection of the propulsion system, the design of the propulsion system, the construction of the propulsion system, the testing of the propulsion system, the flight of the propulsion system, the evaluation of the propulsion system, and the improvement of the propulsion system. 10. The tenth step is the development of a new propulsion system. This includes the selection of the mission requirements, the selection of the propulsion system, the design of the propulsion system, the construction of the propulsion system, the testing of the propulsion system, the flight of the propulsion system, the evaluation of the propulsion system, and the improvement of the propulsion system.

Advanced Chemical Propulsion

Space is a harsh environment. The vacuum of space is a hostile place for most chemical propulsion systems. However, chemical propulsion systems are still the most common type of propulsion system used in space. This is because chemical propulsion systems are simple, reliable, and have a long history of successful use in space.

Aeroplasm

Aeroplasm is a new type of propulsion system. It is a hybrid of a chemical propulsion system and a plasma propulsion system. Aeroplasm systems use a chemical reaction to create a plasma, which is then accelerated by a magnetic field. This results in a high-thrust, high-specific-impulse propulsion system.

Electric Propulsion

Electric propulsion systems use electricity to accelerate ions or electrons. This results in a high-specific-impulse propulsion system. Electric propulsion systems are used for deep space missions, where the high specific impulse is needed to overcome the gravitational pull of the Earth.

Solar Sail Propulsion

Solar sail propulsion is a new type of propulsion system. It uses the pressure of sunlight to accelerate a large, thin, reflective sail. This results in a high-specific-impulse propulsion system. Solar sail propulsion is used for deep space missions, where the high specific impulse is needed to overcome the gravitational pull of the Earth.

Emerging Propulsion Technologies

There are many emerging propulsion technologies that are being developed. These include nuclear propulsion, antimatter propulsion, and laser propulsion. These technologies have the potential to revolutionize space travel by providing high-thrust, high-specific-impulse propulsion systems.

www.nasa.gov/propulsion

Encountering the Old Mythology on Wings of New Technology

NASA